

Applicant: WEYCO GROUP
333 W. ESTABROOK BLVD,
GLENDALE. WI 53212
Attn: WINNIE HUANG

Date: Sep 11, 2018

Sample Description:


- Six (6) groups of submitted samples said to be:
- (A) One (1) pair of TC-288 Black Outsoles
 - (B) One (1) pair of TC-288 Grey Midsoles
 - (C) Two (2) pieces of Black 1.46mm action leather
 - (D) Two (2) pieces of TC-288 3mm Black rubber sheets
 - (E) Two (2) pieces of TC-288 6mm Black rubber sheets
 - (F) Two (2) pieces of TC-288 10mm White rubber sheets.

Style No./Name : M PILLAR ZIPPER CT WP
P.O. No. : Sample
Buyer's Name : Weyco Group
Vendor : BOGS
Supplier : ZhenShen, PrimAsia
Manufacturer : New Star
Ref. : Colour: Black
Country Of Origin : CN
Goods Exported To : U.S.A.
Date Received/Date Test Started: Sep. 06, 2018
Date Final Information Confirmed: --


Test Result Please Refer To Attached Page(S).

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch



Huang Ning, Andy
Assistant General Manager



Footwear Protecting Against Chemicals(Upper) (EN 13832-2:2006, 6.2 & EN 13832-1:2006, 4.2, Modified)

Sample C

Test 1		Chemical Used	Sodium Hydroxide Solution 30% D=1.33			
Test Piece	Letter code		K			
	Test		Before Degradation	After Degradation	Requirement (After Degradation)	Pass/Fail
	1	Upper	Appearance Change	-	Very Slight Change On The Surface Which Is In Contact With The Chemical	-
Tear Resistance (N)			113.9	114.3	≥ 96 N	Pass
2	Upper	Appearance Change	-	Very Slight Change On The Surface Which Is In Contact With The Chemical	-	-
		Tear Resistance (N)	107.1	118.3	≥ 96N	Pass

NOTE

Letter code	Chemical
B	Acetone
D	Dichloromethane
F	Toluene
G	Diethylamine
H	Tetrahydrofurane
I	Ethyl Acetate
J	n- Heptane
K	Sodium Hydroxide Solution 30% D=1.33
L	Sulfuric Acid 95% D=1.84
M	Nitric Acid (65±3)%
N	Acetic Acid (99±1)%
O	Ammonia Solution (25±1)%
P	Hydrogen Peroxide (30±1)% V/V
Q	Isopropanol
R	Sodium Hypochlorite (13±1)%(Of Active Chloride)

End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

